



# **EUREKA+** **TECHNOLOGIES**

«Eureka+» technological process  
International Patent Registered PCT/  
IB2019/050787

**ENVIRONMENTAL AND SUPER-EFFICIENT  
PROCESSING OF WASTE ACTIVATED  
CARBON AT GOLD RECOVERY FACTORIES**



**FROM CARBON FINES TO  
GOLD BARS**

## **SUMMARY**

|   |           |
|---|-----------|
| <b>Introduction .....</b>   | <b>3</b>  |
| <b>«Eureka+» phase I - new technology .....</b>                                       | <b>4</b>  |
| <b>A simple but smart process.....</b>  | <b>5</b>  |
| <b>«Eureka+» phase II .....</b>   | <b>6</b>  |
| <b>«Eureka+» and new electrolysis technology .....</b>                                | <b>7</b>  |
| <b>Key Points of «Eureka+» Phase II .....</b>   | <b>8</b>  |
| <b>Flowsheet of the electrolysis line .....</b>                                       | <b>9</b>  |
| <b>3D view of new industrial electrolysis technical with cartridge and resin.....</b> | <b>10</b> |
| <b>«Eureka+» technology flowsheet from fine carbon to golden bars.....</b>            | <b>11</b> |
| <b>Conclusion .....</b>   | <b>12</b> |
| <b>Annex No. 1. International patentability of technology .....</b>                   | <b>13</b> |



## **Introduction**

**E**very industrial gold deposit in the world has been using cyanide in its technologies for the extraction of gold and silver from ores for more than a hundred years. Thus, the cyanidation process is well established and is the main method used worldwide for gold mining. However, the mining industry has been looking for alternatives to cyanidation for many years, and currently there is no substitute that is more effective, easier to use, less costly, and safer for human health and the environment.

Cyanidation is a chemical process, as opposed to physical processes such as gravity. The mining industry uses cyanidation to extract fine gold from ores. The method is based on the principle of activated carbon leaching in columns or tanks.

Activated carbon effectively extracts gold from cyanide, as gold is adsorbed into the pores of the carbon. This has led to technologies such as CIP (coal in pulp), CIL (coal in leachate) and CIC (coal in columns).

It should be noted that in all methods, during the extraction of gold with cyanide, specific wastes containing precious metals (gold, silver, copper, etc.) are formed as a result of the decomposition of activated carbon, which is inherent in the chemical process of cyanidation.



**The «EUREKA +» technology is the correct and only answer to the question of processing waste carbon fines to gold bars, which consists of 2 phases.**

**T**he gold content of these activated carbon tailings varies greatly from 100 grams per ton to 1 kg. per ton.

**W**ith gold prices below \$1,000 USD per ounce until 2010, industrial gold mines were not interested in recycling waste activated carbon. However, with the price of an ounce of gold between 1800 and 2000 US dollars, the economy of enterprises is increasingly interested in processing also additional raw materials in the form of waste activated carbon.

**W**ith the development of environmental friendliness in the production system of gold mines and the ever-increasing value of activated carbon waste, a new environmentally friendly, efficient and innovative processing technology had to emerge.

## «Eureka+» phase I - new technology

Activated carbon, in the process of sorption, desorption and reactivation, loses its qualities and becomes too small to be reused in the adsorption leaching process, so it is removed and no longer used in the process.

Waste activated carbon of low quality contains an average of 50-500 grams of gold per ton, although in real conditions this figure can vary from 30-1000 grams of gold per ton. The gold mining companies are forced to constantly increase the volume of gold mining, so sooner or later they come to the decision that it is necessary to extract gold from fine coal waste as well.

By making small changes to the production process to capture as much of the lower quality activated carbon as possible, gold refineries can quite easily recover significant amounts of gold from the production waste. However, this requires a reliable and inexpensive method for extracting gold from fine coal waste.

VALOR CANADA INC. introduces the new patented «EUREKA+» technology, a technical solution that has completely changed the way gold is extracted from uncalibrated activated carbon particles.

**The equipment «EUREKA +» provides original technical solutions: the conversion of powdered activated carbon waste into granules for optimal and controlled combustion.**




## A SIMPLE BUT SMART PROCESS

The «EUREKA +» plant uses advanced high-temperature combustion technology using two chambers: one for combustion, the second for the gas and dust afterburning system. The burning process is accompanied by a heat exchanger and a special filter.

The above scheme allows the release of gold from coal into fly ash, which is then captured by a high efficiency filter. The product collected in the filter is incinerated again, since its carbon content is 1% higher. It should be noted that all produced and received gold concentrate must contain less than 1% carbon.

The entire waste activated carbon recycling process is fully automated, which maximizes plant productivity.

The «EUREKA +» technology guarantees the degree of extraction of 98-99% of the gold contained in the waste carbon fines.





## «EUREKA +» PHASE II

**T**he gold concentrate obtained from carbon fines by high quality controlled roasting with a very low percentage of carbon (C) and sulfide (S) is further processed by leaching with a cyanide solution and electrolysis in a special cartridge designed for the production of gold bars.



## «EUREKA +» AND NEW ELECTROLYSIS TECHNOLOGY

**A**fter obtaining the gold-bearing concentrate using the «EUREKA+» technology, phase I, the second stage is implemented, that is, phase II: leaching + electrolysis.

- The resulting gold concentrate is processed on a new electrolysis line, where the extraction of precious metals takes place in disposable special cartridges, which are melted directly in the process of making gold bars. To achieve a recovery close to 100%, the waste from the electrolysis line is treated on resin filters, which are also melted. The final electrolysis emissions are neutralized at the end of the process, which allows them to be disposed of without danger to humans and the environment.

**The new compact and reliable electrolysis line provides optimum recovery of precious metals.**



Fig.1 A special electrolysis cartridge in which gold is collected is remelted to produce gold bars.






Fig.2 Electrolysis system

## KEY POINTS OF «EUREKA +» PHASE II


- **T**he obtained high-quality gold-bearing concentrate according to the «EUREKA +» technology according to phase No.I allows it to be processed further by leaching in a cyanide solution and electrolysis in a special cartridge.
- Controlled burning makes it possible to destroy the matrix of the sulfide particle and create channels for supplying leaching reagents to fine gold. Reduction of sulfide content to less than 2% and carbon content to less than 1% allows leaching treatment in cyanide solution with recovery factors up to +95%.
- Pre-treatment with oxygen prior to the addition of cyanide has a beneficial effect on the kinetics of cyanidation.
- The leaching time in the cyanide solution varies from 6 to 12 hours, depending on the physical and chemical parameters of the processed gold concentrate.
- The use of lead denitrate has a beneficial effect on the efficiency of cyanidation and on its kinetics, providing better dissolution of gold due to the removal of sulfur ions by precipitation of PbS.
- This results in better cyanide ion availability and reduced passivation of gold surfaces.
- All these points are summed up and make it possible to obtain a gold recovery factor of +95% and does not require too fine grinding of the gold-bearing concentrate, 100 microns is enough.
- Grinding the gold concentrate too fine in the leaching process causes many costly problems downstream.
- High quality gold concentrate ( $S < 2\%$ ,  $C < 1\%$ ) + oxygenation before cyanide injection + lead denitrate = maximum recovery and low costs.  
The extraction of precious metals by electrolysis is carried out in special cartridges that do not contain metal elements. Cartridges after filling are melted down directly for the manufacture of gold bars.
- There are two models of disposable cartridges: 2 and 5 kg. precious metals. An ion exchange filter at the end of the electrolysis line optimizes the extraction of precious metals.
- After filling with precious metals, the ion-exchange filter is placed further into the melt to obtain bars.



Flowsheet of the gold extraction line by industrial electrolysis using a cartridge and resin




Smelting gold bars




|  |          |   |           |
|--|----------|---|-----------|
| <b>BAT</b>   | CLIENT : | RDC : 1750  | Ind. : 00 |
| Date :   |          | Signature :   |           |
| <b>Valor Canada Inc., 1632,<br/>Place de Nantes,<br/>Saint-Lazare, QC 17T3MS,<br/>Canada,<br/>Tel. w/a: +996 700 12 45 17<br/>e-mail:<br/>valor.canada.inc@gmail.com</b> |          | <br><b>EUREKA+</b><br>TECHNOLOGIES |           |

3D view of the line of a new industrial  
electrolysis method using special  
cartridges and resin



|  |          |             |      |   |    |
|--|----------|-------------|------|---|----|
| <b>BAT</b>   | CLIENT : | RDC :       | 1750 | Ind. :  | 00 |
| Date :   |          | Signature : |      |   |    |
| <p>Valor Canada Inc., 1632,<br/>Place de Nantes,<br/>Saint-Lazare, QC 17T3MS,<br/>Canada,<br/>Tel. w/a: +996 700 12 45 17<br/>e-mail:<br/>valor.canada.inc@gmail.com</p> |          |             |      |  |    |

## FLOWSHEET OF «EUREKA +» TECHNOLOGY PROCESSING FROM CARBON FINES TO GOLD BAR



## CONCLUSION

- **The «EUREKA +» technology** is a true new patented method for extracting gold from waste activated carbon. The system has successfully proven itself with the installation of a line in Central Asia (Kumtor mine in Kyrgyzstan).

The system uses the process of roasting prepared pellets from waste carbon fines, after which a gold concentrate with a carbon content of less than 1% and a sulfur content of less than 2% is obtained, and a new intelligent electrolysis process with special cartridges is used.

- **HIGH RECOVERY**

With recovery rates ranging from 97 to 99%, our system is far superior to other industrial processes.

- **CONTINUOUS OPERATION**

The developed system operates in a continuous mode, the productivity is 130/150 kg/h or processing from 35 to 40 tons of raw materials per month. In addition, you need to consider the time for start-up and maintenance.

- **LOW OPERATING COSTS**

«EUREKA +» is a thermal process that also uses the heat generated during the roasting of granulated carbon fines, thereby optimizing the controlled self-combustion provided by the production of high-quality and high-calorie granules. This results in very low operating costs, allowing gold to be recovered at ultra-low concentrations.

- **RELIABILITY AND SERVICE**

The simplified design with standard equipment reduces the need for maintenance and increases uptime.

- **ECOLOGY**

High-temperature burning, the use of special filters and an intelligent and efficient electrolysis system all contribute to the implementation of the process without harming the environment.



## **INTERNATIONAL TECHNOLOGY PATENT**

---

**Australian Patent  
No201942673  
PCT  
WO2020/157543**





28 July 2021

## Notice of acceptance for patent application

Delivering a world leading IP system

Phone: 1300 651 010  
International: +61 2 6283 2999

[www.ipaustralia.gov.au](http://www.ipaustralia.gov.au)

ABN: 38 113 072 755

**Pizeys Patent and Trade Mark Attorneys Pty Ltd**  
PO Box 291  
WODEN ACT 2606  
Australia

|                           |                |
|---------------------------|----------------|
| <b>Your reference</b>     | 70298GRA/JL/KJ |
| <b>Application number</b> | 2019426739     |
| <b>Applicant name</b>     | Yvan Grac      |

Dear Pizeys Patent and Trade Mark Attorneys Pty Ltd,

This patent application was accepted on 16 July 2021. The accepted specification incorporates the following amendments:

PCT: WO2020/157543

The total number of claims at acceptance has been reported as: 8

Notice of the acceptance will appear in the Australian Official Journal of Patents on 12 August 2021.

Please review the acceptance details attached to this letter to ensure that they are correct. If you wish to amend any details prior to the grant please do so within 3 months of the advertisement of acceptance.

An Invitation to Pay (ITP) the acceptance fee will be issued to you. This fee will include an additional component if the number of claims exceeds 20.

Details of this patent application can be viewed on [AusPat](http://AusPat), our Australian patent search database.

Yours sincerely,

IP Australia

## Standard patent details

|  |   |
|--|---|
| <b>Patent number:</b>                  | 2019426739  |
| <b>Title:</b>                          | Process for recovering non-ferrous precious metals by pelletisation and calcination of leaching activated carbon powder |
| <b>Your reference:</b>                 | 70298GRA/JL/KJ  |
| <b>Number of claims at acceptance:</b> | 8   |

## Applicant and inventor details

### **Applicant name(s) and address(es)** *(as it will appear on certificate/s)* :

Yvan Grac of 33/1 Razzakova Street, Appart 30 Bishkek 720040 Kyrgyzstan

**Inventor name(s):** GRAC, Yvan

## Agent details

|                                    |   |
|------------------------------------|---|
| <b>Agent Name</b>                  | Pizzeys Patent and Trade Mark Attorneys Pty Ltd |
| <b>Address for correspondence:</b> | PO Box 291<br>WODEN ACT 2606<br>Australia       |
| <b>Address for legal service:</b>  | PO Box 291<br>WODEN ACT 2606<br>Australia       |

## Prior art details

**Prior art documents:**  
CN 106498178 A

## Priority details

**Priority details:** None

## International classification

C22B 1/24 (2006.01)  
C22B 3/24 (2006.01)  
C22B 7/02 (2006.01)  
C22B 11/02 (2006.01)  
C22B 11/08 (2006.01)

---

Relevant dates

---

**Acceptance date:** 16 July 2021  
**Acceptance to be advertised:** 12 August 2021  
**Complete filing date:** 31 January 2019  
**OPI date:** 6 August 2020  
**Continuation fee due date:** 31 January 2023  
**Date of patent:** 31 January 2019  
**Expiry date:** 31 January 2039  
**National phase entry date:** 1 June 2021



**VALOR CANADA INC.**

## **Contacts:**

Valor Canada Inc., 1632, Place de Nantes,  
Saint-Lazare, QC 17T 3MS, Canada,  
Tel. w/a: +33 6 49 35 11 35

e-mail: [valor.canada.inc@gmail.com](mailto:valor.canada.inc@gmail.com)

